



West Yorkshire Materials Testing Service

PO Box 5, Morley, LS27 0QP
Nepshaw Lane South, Morley, Leeds
Tel 0113 253 0241 Fax 0113 252 7029
Head of Laboratory G. Briggs C. Text ATI

Page 1 of 1

Client: Southcombe Brothers
Stoke-Sub-Hamden
Somerset
TA14 6QD

Entry No: 38291-01

Date Received: 8th April 2009

Client's Description: USAR Glove

TEST REPORT

Tests Required: EN 388

Test	Test Method	Test Result	EN 388 Level Achieved
Abrasion	EN 388 Para 6.1	2,100 rubs	3
Blade Cut	EN ISO 13997	33.2N	Equivalent to Level 5
Tear Resistance	EN 388 Para 6.3	Palm - Length 87N Width 88N Lining - Length 69N Width 73N	5
Puncture Resistance	EN 388 Para 6.4	139.1N	3

Note: The blade cut and puncture resistance tests were subcontracted to a UKAS Accredited Laboratory.

-----End of Document -----

This is hereby certified to be a correct return of the tests made of the items referred to herein.



1104

G Briggs
Head of Laboratory
3rd June 2009

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

